



Technical Datasheet

Product Name	Product Code
TM TOP HB	A XA 136

Texbond
nonwovens

material	type	feature	colour
Laminate	S/F/S	UV, barrier	anthracite/anthracite

Properties

Properties	Dir.	Unit	Method	Typical value
Mass per unit area	-	g/m ²	EN 1849-2	136
Tensile strength	MD	N/5cm	EN 12311-2*	260
Tensile strength	CD	N/5cm	EN 12311-2*	200
Elongation at break	MD	%	EN 12311-2*	90
Elongation at break	CD	%	EN 12311-2*	95
Tear strength (nail shank)	MD	N	EN 12310-1*	140
Tear strength (nail shank)	CD	N	EN 12310-1*	180
Water penetration resist.	-	cm	EN 20811	> 300
Resistance to water penetration	-	-	EN 1928, method B (2 kPa, 24 h)	watertight
Sd-value	-	m	EN ISO 12572	> 2
UV stability	-	months	-	4
Temperature resistance	-	°C	-	- 40 / + 80

*Folded samples ad per EN13984
BL3

The figures provided in this datasheet are consistent with the current state of our knowledge, and are intended to provide general information on our product and its applications. They are not a guarantee of any specific product attribute or the suitability of the product for a specific application.

issue date: 3/4/2008 7:35:00 PM