



Texbond
nonwovens

Technical Datasheet	
product	ULTRATEX
type	C

	weight	tensile strength		elongation at break		tear strength	
method	TEXBOND	EDANA 20.2-89		EDANA 20.2-89		EDANA 70.4-99	
unit	g/m ²	N/5cm	N/5cm	%	%	N	N
direction	-	MD	CD	MD	CD	MD	CD

typical values*	14	26	18	55	58	12	16
	15	28	19	55	58	12	16
	16	30	20	55	58	13	17
	17	32	22	55	58	14	18
	18	34	23	55	58	15	19
	20	36	26	55	58	17	20
	25	45	32	60	63	19	24
	30	55	41	60	63	23	29
	35	65	50	60	63	26	36
	40	85	63	65	68	30	40
	50	110	80	65	68	37	50
	60	125	95	70	73	47	55
	70	140	110	75	78	55	60
	80	150	128	70	73	58	65
	90	160	135	65	68	60	68
100	170	145	60	63	65	70	

* actual values depend on the colour, additives and PP resin type

The figures provided in this datasheet are consistent with the current state of our knowledge, and are intended to provide general information on our product and its applications. They are not a guarantee of any specific product attribute or the suitability of the product for a specific application.