



**Texbond**  
nonwovens

<b>Technical Datasheet</b>	
Product	<b>ULTRATEX</b>
Type	<b>D</b>

	<b>weight</b>	<b>tensile strength</b>		<b>elongation at break</b>		<b>tear strength</b>	
method	TEXBOND	EDANA 20.2-89		EDANA 20.2-89		EDANA 70.4-99	
unit	g/m <sup>2</sup>	N/5cm	N/5cm	%	%	N	N
direction	-	MD	CD	MD	CD	MD	CD

<b>typical value*</b>	12	29	15	55	60	7	12
	13	31	17	55	60	8	13
	14	33	18	55	60	8	14
	15	36	19	55	60	9	15
	16	38	20	56	61	10	16
	17	41	21	56	61	11	17
	18	43	23	56	61	12	18
	20	50	25	57	62	14	20
	25	58	33	58	63	16	25
	30	74	40	59	64	20	30
	35	84	48	60	65	24	35
	38	90	52	60	65	26	38
	40	96	56	59	64	28	40
	50	112	71	57	62	34	50
	60	127	84	50	60	40	60
70	143	90	50	60	47	70	

\* actual values depend on the colour, additives and PP resin type

The figures provided in this datasheet are consistent with the current state of our knowledge, and are intended to provide general information on our product and its applications. They are not a guarantee of any specific product attribute or the suitability of the product for a specific application.

issue date : 18/02/11